

Formulary

SilikMira Max

Product description: Crème Eyeshadow

Phase	Trade Name	INCI Name	Supplier	Formula #	Formula #	Formula #	Formula #
				212-88A	212-88B	212-88C	212-88D
A	Floraester IPJ	Isopropyl Jojobate (and) Jojoba Alcohol (and) Jojoba	Florotech	18.99	18.99	18.99	18.99
	Puresyn 2	Hydrogenated Poly(C6-14 Olefin)	Sandream Impact	6.71	6.71	6.71	6.71
	Floramac 10	Ethyl Macadamiate	Jarchem	14.40	14.40	14.40	14.40
	Permethyl 99	Isododecane	Presperse	5.00	5.00	5.00	5.00
	Jeenate 2H	Polyethylene	Jeen	4.89	4.89	4.89	4.89
	Jeenate 5H	Polyethylene	Jeen	4.00	4.00	4.00	4.00
	SP 220	Cetyl Esters	Strahl and Pitch	2.45	2.45	2.45	2.45
B	Sansil 5012	Cyclopentasiloxane and Dimethicone Copolymer	Sandream Impact	12.86	12.86	12.86	12.86
	Vitamin E Oil	Tocopheryl Acetate	Sandream Impact	0.20	0.20	0.20	0.20
	Mica LL3	Mica, Lauroyl Lysine	Sandream Impact	5.00	5.00	5.00	5.00
	HDK H30	Hydrophobic Pyrogenic Silica	Wacker Chemical Corp	0.50	0.50	0.50	0.50
C	SilikMira Max GYB	Silica, TiO2, Iron Oxides, Synthetic Fluorphlogopite, SnO2	Sandream Impact	25.00			
	SilikMira Max ROG	Silica, TiO2, Iron Oxides, Synthetic Fluorphlogopite, SnO2	Sandream Impact		25.00		
	SilikMira Max PGO	Silica, TiO2, Iron Oxides, Synthetic Fluorphlogopite, SnO2	Sandream Impact			25.00	
	SilikMira Max VPG	Silica, TiO2, Iron Oxides, Synthetic Fluorphlogopite, SnO2	Sandream Impact				25.00
	SilikMira Max VBR	Silica, TiO2, Iron Oxides, Synthetic Fluorphlogopite, SnO2	Sandream Impact				
	SilikMira Variable TBV	Silica, Titanium Dioxide, Iron Oxides, Synthetic Fluorphlogopite, Ferric Ferrocyanide	Sandream Impact				
TOTAL PERCENT				100.00	100.00	100.00	100.00

Procedure: Weigh all of phase A into glass beaker and heat to 80°C. Mix with propeller and continue mixing until solution is homogenous. Add phase B and slowly mix until uniform. Add phase C to A and B and rapidly mix until uniform. Dispense into pots or vials and cool to room temperature.