



**Formulary**  
**July 2021 Newsletter- "Tickled Pink"**  
**New Sachet CF Pinks**

**Product Description: Creamy Eye & Blush Powder**

Phase	Trade Name	INCI Name	Supplier	Formula # 215-08	Formula # 215-09	Formula # 215-21
A	SanTalc AV	Talc, Aloe Barbadensis Leaf Extract	Sandream Specialties	17.48	17.48	17.48
	SanMica AV	Mica, Aloe Barbadensis Leaf Extract	Sandream Specialties	14.46	14.46	14.46
	Biluna 2600 UVS	Bismuth Oxychloride	Sandream Specialties	4.80	4.80	4.80
	Micropoly 250S	Polyethylene	Micro Powders Inc.	3.60	3.60	3.60
	Zinc Stearate	Zinc Stearate	Brenntag	3.60	3.60	3.60
	Aerosil R972	Fumed Silica	Aerosil	0.06	0.06	0.06
B	Sachet CF Rose (S8183)	Synthetic Fluorphlogopite, Titanium Dioxide, Iron Oxides, Tin Oxide	Sandream Specialties	44.00		
	Sachet CF Magenta (S8193)	Synthetic Fluorphlogopite, Titanium Dioxide, Iron Oxides, Tin Oxide	Sandream Specialties		44.00	
	Sachet CF Fuchsia (S8203)	Synthetic Fluorphlogopite, Titanium Dioxide, Iron Oxides, Tin Oxide	Sandream Specialties			44.00
C	Vitamin E Acetate	Vitamin E Acetate	Sandream Specialties	0.75	0.75	0.75
	Octyldodecyl Olivatate	Octyldodecyl Oleate	Sandream Specialties	4.50	4.50	4.50
	Beeswax SP-422P	Beeswax	Stahl and Pitsch	0.15	0.15	0.15
	Wickenol 171	Ethylhexyl hydroxystearate	Alzo	4.50	4.50	4.50
	Jeecide Phenoxy	Phenoxyethanol	Jeen	1.50	1.50	1.50
	Propyl Paraben	Propyl Paraben	Sandream Specialties	0.15	0.15	0.15
	Methyl Paraben	Methyl Paraben	Sandream Specialties	0.45	0.45	0.45
<b>TOTAL PERCENT</b>				100.00	100.00	100.00

**Procedure:** Premix Phase A in osterizer blender and mix thoroughly until well blended. Add phase B to A and gently mix for 1 minute. Preweigh phase C into glass beaker and heat to 70°C and stir until all is dissolved and uniform. Add phase C to A and B and blend for one minute. Scrape down sides and repeat blending process. Press into desired eyeshadow pans.

The information provided is furnished without warranty, expressed or implied, except that it is accurate to the best knowledge of Sandream Specialties. Customers should utilize formulations provided as a guide and perform in-house stability, micro and other necessary testing.