

**Color Corrector Pen**

**Lab #**

**NB#222-16**

Phase	RM (Trade Name)	INCI Name	Supplier Name	A	B	C
A	NOO Crystal	Octyldodecyl Oleate, Tocopheryl Acetate	Sandream	13.2	13.2	13.2
A	Jarcol 120CG	Octyldodecanol	Jarchem	13	13	13
A	Jeesilc PTMF	Phenyltrimethicone	Jeen	10	10	10
A	Softsan 649	Bis-diglyceryl Polyacyladipate	N/A	6	6	6
A	Snow White Petrolatum	Petrolatum	Penreco	6	6	6
A	Jeenate 3H	Polyethylene	Jeen	5	5	5
A	Beeswax SP-422P	Beeswax	Strahl & Pitsch	5.5	5.5	5.5
A	Carnauba Wax SP-63	Copernicia Cerifera	Strahl & Pitsch	4.8	4.8	4.8
A	Candellila SP-75	Euphorbia Cerifera	Strahl & Pitsch	3	3	3
A	Paraffin SP-227B	Paraffin	Strahl & Pitsch	2	2	2
A	Vitamin E	Tocopheryl Acetate	Sandream	1.5	1.5	1.5
B	Bichroma Red	Bismuth Oxychloride, Mica, Iron Oxides	Sandream	9		
B	SD Soft Red	Mica, TiO2, SiO2, SnO2	Sandream	3		
B	Bichroma Green	Bismuth Oxychloride, Mica, Chromium Oxide Greens, Calcium Stearate	Sandream		9	
B	SD Soft Green	Mica, TiO2, SiO2, SnO2	Sandream		3	
B	Bichroma Violet	Bismuth Oxychloride, Mica, Manganese Violet, Magnesium Stearate	Sandream			9
B	SD Soft Violet	Mica, TiO2, SiO2, SnO2	Sandream			3
C	Fancol ID-CG	IDD	Elementis	18	18	18
				100	100	100

**Procedure**

- 1 Weigh all of phase A into a glass beaker and heat to 90C
- 2 Mix with propeller and continue mixing until all raws are dissolved and solution is homogenous
- 3 Add Phase B and slowly mix until uniform. Lower temperature to 80C
- 4 Slowly add Phase C
- 5 Cover and mix until uniform
- 6 Pour into molds, freeze for 10 minutes for easy release