

Glamour Party Eyeshadow - Teal

Lab # 223-45

Phase	Name	INCI	Function	Supplier	%
A	DI Water	Water	-	-	66.30
	Glycerin 99.7% USP	Glycerin	Humectant	Univar	5.20
	Zemea® Propandiol	Propandiol	Humectant	CovationBio	1.70
	Carbopol® Ultrez 20	Acrylates, C10-30 Alkyl Acrylate Crosspolymer	Film Former	Lubrizol	0.46
B	Simugel™ NS	Hydroxyethyl Acrylate, Sodium Acryloyldimethyl Taurate Copolymer, Squalane, Polysorbate 60	Thickener	Seppic	1.36
	10% NaOH	Water, Sodium Hydroxide	pH	-	2.50
	Jeecide Phenoxy	Phenoxyethanol	Preservative	Vantage	1.00
C	SanSilica 307	Silica	Texture	Sandream Specialties	8.00
	Glamour Party Green	Calcium Aluminum Borosilicate, Titanium Dioxide, Tin Oxide, Iron Oxide Red, Ferric Ferrocyanide	Pearl		5.74
	Glamour Party Blue	Calcium Aluminum Borosilicate, Titanium Dioxide, Tin Oxide, Ferric Ferrocyanide	Pearl		7.74
Total					100.00

Procedure

1	Add Phase A to a beaker and propeller mix at 500 rpm until uniform.
2	Add Phase B to the beaker and continue mixing at 500 rpm until uniform.
3	Add Phase C to the beaker and mix at 300 rpm until texture is smooth.
4	Adjust pH if necessary and pack into airless containers.

Notes

pH 6.5-7